

DP4

Maintenance-free



Quality

All the products described in this handbook are manufactured under DIN ISO 9001/2 or TS 16949 approved quality management systems.



CERTIFICATE

DQS GmbH
Deutsche Gesellschaft zur Zertifizierung von Managementsystemen
herby certifies that the company

GLACIER GARLOCK BEARINGS GMBH & CO. KG
Ochsenbrunnstraße 9
D-74078 Heilbronn
Germany

with the production sites as listed in the annex
for the scope

Manufacture and distribution of plain bearings for the automotive industry
and other industrial applications with design at
GLACIER GARLOCK BEARINGS E U R L Anney, France

has implemented and maintains a
Quality Management System.

An audit, conducted in accordance with the "Rules for certification bodies to ISO/TS 16949:2002 First Edition"
and documented in a report, has verified that this quality management system fulfills the requirements
of the following ISO Technical Specification including ISO 9001:2000:

ISO/TS 16949:2002
Second Edition March 2002



CERTIFICATE

DQS GmbH
Deutsche Gesellschaft zur Zertifizierung von Managementsystemen
herby certifies that the company

GLACIER GARLOCK BEARINGS GMBH & CO. KG
Ochsenbrunnstraße 9
D-74078 Heilbronn
Germany

GLACIER GARLOCK BEARINGS DO BRASIL LTDA
Avenida Gupe 10787
BR-06422-120 Barueri, Sao Paulo
Brasil

for the scope

Manufacture and distribution of plain bearings for the automotive industry
and other industrial applications with design at
GLACIER GARLOCK BEARINGS E U R L Anney, France

has implemented and maintains an
Environmental Management System.

An audit, documented in a report, has verified that this
environmental management system fulfills the requirements
of the following standard:

DIN EN ISO 14001
October 1996 edition



CERTIFICATE

DQS GmbH
Deutsche Gesellschaft zur Zertifizierung von Managementsystemen
herby certifies that the company

GLACIER GARLOCK BEARINGS GMBH & CO. KG
Ochsenbrunnstraße 9
D-74078 Heilbronn
Germany

GLACIER GARLOCK BEARINGS DO BRASIL LTDA
Avenida Gupe, 10787

for the scope

Manufacture and distribution of plain bearings
and other industrial applications at
GLACIER GARLOCK BEARINGS E U R L

has implemented and maintains a
Quality Management System.

An audit, documented in a report, has
verified that this quality management system fulfills II
of the following standards:

DIN EN ISO 9001 :
December 2000 edition

This certificate is valid until
Certificate Registration No.:
Frankfurt am Main, Berlin

CERTIFICATION

N° ENV/2003/21538

Le Système de Management Environnemental ISO14001 par :
The Environmental Management System developed by :

GLACIER GARLOCK BEARINGS

pour les activités suivantes :
for the following activities :

**INDUSTRIALISATION, FABRICATION ET VENTE
DE SYSTEMES ANTI-FRICTION.**

**INDUSTRIALIZATION, MANUFACTURING AND SALES
OF ANTI-FRICTION SYSTEMS.**

exercées sur le(s) site(s) suivant(s) :
carried out in the following location(s) :

**65, chemin de la prairie BP n°2074 F-74008 ANNIÉCY
2326, rue Henri Barbusse F-92110 CLICHY**

a été évalué et jugé conforme aux exigences de la norme :
has been assessed and found to conform to the requirements of the standard :


ISO 14001 (1996)

Le certificat correspondant a été délivré dans les conditions listées par AFAG, à :
The corresponding certificate has been delivered under AFAG application rules, on :

2003-12-29	2006-12-29
------------	------------

Le Président du Comité de Certification Le Directeur Général d'AFAG Le Représentant de l'Entreprise
The President of the Certification Committee The Managing Director of AFAG On Behalf of the Firm

P. SCHWARTZMANN O. PEYRAT J.-ZATTARA



CERTIFICATE

N° TS/2003/21286
N° IATF : 0017381

AFAG certifie que le système qualité adopté par :
AFAG certifies that the quality system developed by :

GLACIER GARLOCK BEARINGS

pour les activités suivantes :
for the following activities :

**CONCEPTION, INDUSTRIALISATION, FABRICATION ET VENTE
DE SYSTEMES ANTI-FRICTION.**

**INDUSTRIALISATION, FABRICATION ET VENTE
DE PALIERS DE POMPES HYDRAULIQUES A ENGRENAGES.**

**DESIGN, DEVELOPMENT, MANUFACTURING AND SALES
OF ANTI-FRICTION SYSTEMS.**

**DEVELOPMENT, MANUFACTURING AND SALES
OF HYDRAULIC GEAR PUMP BEARINGS BLOCKS.**

exercées sur le (les) site(s) suivant(s) :
carried out in the following location(s) :

**65, chemin de la prairie BP n°2074 F-74008 ANNIÉCY
Route de Saint-Avoird Zone Industrielle F-92750 DIEULIZE
23-26, rue Henri Barbusse F-92210 CLICHY
(Liste des sites en annexes n° 1 à n° 2)**

a été évalué selon les "Règles pour les certifications dans le cadre de la certification automobile AFAG" (TS/2003/21286) 2002 - Première édition
has been assessed in accordance with "The rules for the certification bodies for the automotive certification from ISO/TS 16949 2002 - First edition"

ISO/TS 16949 : 2002

Chapitre de l'ISO/TS 16949 2002 amendement non applicable 7.3 (Prescription de la conception des processus de fabrication) n'est pas autorisé
The ISO/TS 16949 2002 chapter which are not applicable 7.3 (prescription of the fabrication process design) is not authorized

Néant

Le présent certificat, délivré dans les conditions listées par AFAG, est valide à date de :
This certificate, delivered under AFAG rules, is valid as from :

2003-11-07

Validité (date de début) jusqu'au (date fin) date (month-year)

2006-11-06

Le Président du Comité de Certification Le Directeur Général d'AFAG Le Représentant de l'Entreprise
The President of the Certification Committee The Managing Director of AFAG On Behalf of the Firm

M. FONDEVOLLE O. PEYRAT J.-ZATTARA

Formula Symbols and Designations

Formula Symbol	Unit	Designation
A	mm^2	Surface area of DP4 bearing
A_M	mm^2	Surface area of mating surface in contact with DP4 bearing (slideway)
a_B	-	Bearing size factor
a_C	-	Application factor for bore burnishing or machining
a_E	-	High load factor
a_{E1}	-	Specific load factor (slideways)
a_{E2}	-	Speed, temperature and material factor (slideways)
a_{E3}	-	Relative contact area factor (slideways)
a_L	-	Life correction constant
a_M	-	Mating surface material factor
a_T	-	Temperature application factor
B	mm	Nominal bush length
C	$1/\text{min}$	Dynamic load frequency
C_D	mm	Installed diametral clearance
C_i	mm	Inside chamfer
C_o	mm	Outside chamfer
C_T	-	Total number of dynamic load cycles
D_c	mm	Diameter of burnishing tool
D_{fl}	mm	Nominal bush flange OD
D_H	mm	Housing diameter
D_i	mm	Nominal bush and thrust washer ID
$D_{i,a}$	mm	Bush ID when assembled in housing
D_J	mm	Shaft diameter
D_{Nth}	nvt	Max. thermal neutron dose
D_o	mm	Nominal bush and thrust washer OD
d_b	mm	Dowel hole diameter
d_L	mm	Oil hole diameter
d_p	mm	Pitch circle diameter for dowel hole
D_γ	Gy	Max. Gamma radiation dose $G_\gamma = \text{J/kg}$
F	N	Bearing load
F_{ch}	N	Test load
F_i	N	Insertion force
f	-	Coefficient of friction
H_a	mm	Depth of housing recess (e.g. for thrust washers)
H_d	mm	Diameter of housing recess (thrust washers)

Formula Symbol	Unit	Designation
L	mm	Strip length
L_H	h	Bearing service life
L_S	mm	Length of stroke (slideway)
N	$1/\text{min}$	Rotational speed
N_E	$1/\text{min}$	Equivalent rotational speed for oscillating movement
N_{osz}	$1/\text{min}$	Oscillating movement frequency
$\bar{\rho}$	N/mm^2	Specific load
$\bar{\rho}_{lim}$	N/mm^2	Specific load limit
$\bar{\rho}_{sta,max}$	N/mm^2	Maximum static load
$\bar{\rho}_{dyn,max}$	N/mm^2	Maximum dynamic load
Q	-	Number of load/movement cycles
R_a	μm	Surface roughness (DIN 4768, ISO/DIN 4287/1)
R_{OB}	Ω	Electrical resistance
s_3	mm	Bush wall thickness
s_{fl}	mm	Flange thickness
s_S	mm	Strip thickness
s_T	mm	Thrust washer thickness
T	$^\circ\text{C}$	Temperature
T_{amb}	$^\circ\text{C}$	Ambient temperature
T_{max}	$^\circ\text{C}$	Maximum temperature
T_{min}	$^\circ\text{C}$	Minimum temperature
U	m/s	Sliding speed
W	mm	Strip width
W_u	mm	Maximum usable strip width
Z_T	-	Total number of cycles
α_1	$1/10^6\text{K}$	Coefficient of linear thermal expansion parallel to surface
α_2	$1/10^6\text{K}$	Coefficient of linear thermal expansion normal to surface
σ_c	N/mm^2	Compressive yield strength
λ	W/mK	Thermal conductivity
φ	$^\circ$	Angular displacement
η	Ns/mm^2	Dynamic viscosity

Contents

Quality	I	6.3 Characteristics of Lubricated Bearings	23
Formula Symbols and Designations	II	6.4 Design Guidance	24
1 Introduction	4	Explanation to Fig. 24	24
1.1 Characteristics and Advantages	4	6.5 Clearances for lubricated operation	25
2 Structure and Composition	4	6.6 Grooving for lubricated operation	25
2.1 Basic Forms	5	6.7 Mating Surface Finish for lubricated operation	25
Standard Components	5	6.8 Grease Lubrication	25
Non-Standard Components	5	7 Bearing Assembly	26
3 Properties	5	Dimensions and Tolerances	26
3.1 Physical and Mechanical Properties	5	7.1 Allowance for Thermal Expansion	26
3.2 Chemical Properties	6	7.2 Tolerances for minimum clearance	27
3.3 Frictional Properties	6	Sizing	27
Effect of Temperature for unlubricated applications	7	7.3 Counterface Design	28
4 Bearing Performance ...	8	7.4 Installation	29
4.1 McPherson Strut Applications .	8	Fitting of cylindrical Bushes	29
Wear and Friction Properties	8	Fitting of flanged bushes	29
Cavitation Erosion Resistance ..	10	Insertion Forces	29
Flow Erosion Resistance	11	Alignment	30
4.2 Hydraulic Applications	12	Sealing	30
GGB Jupiter Test Rig	12	7.5 Axial Location	30
4.3 Dry Wear Performance	13	Fitting of Thrust Washers	30
Design Factors	13	Slideways	31
Application Factors	15	8 Modification	32
Mating Surface	16	8.1 Cutting and Machining	32
Bore Burnishing	17	Drilling Oil Holes	32
Type of Load	17	Cutting Strip Material	32
4.4 Calculation of Bearing Service Life	18	8.2 Electroplating	32
Specific load \bar{p}	18	DP4 Components	32
High load factor a_E	18	9 Standard Products	33
Modified $\bar{p}U$ Factor	18	9.1 DP4 Cylindrical bushes	33
Estimation of bearing life L_H ..	18	9.2 DP4 Flanged bushes	38
Bore Burnishing	19	9.3 DP4 Thrust Washers	40
Slideways	19	9.4 DP4 Flanged Thrust Washers .	41
4.5 Worked Examples	20	9.5 DP4 Strip	41
5 Data Sheet	21	10 Test Methods	42
5.1 Data for bearing design calculations	21	10.1 Measurement of Wrapped Bushes	42
6 Lubrication	22	Test A of ISO 3547 Part 2	42
6.1 Lubricants	22	Test B (alternatively to Test A) ..	42
6.2 Tribology	22	Test C	42
Hydrodynamic lubrication	22	Measurement of Wall Thickness (alternatively to Test C)	42
Mixed film lubrication	23	Test D	42
Boundary lubrication	23		

1 Introduction

The purpose of this handbook is to provide comprehensive technical information on the characteristics of DP4™ bearings.

The information given permits designers to establish the correct size of bearing required and the expected life and performance.

GGB Research and Development services are available to assist with unusual design problems.

Complete information on the range of DP4 standard stock products is given together with details of other DP4 products.

GGB is continually refining and extending its experimental and theoretical knowledge and, therefore, when using this brochure it is always worth-while to contact the Company should additional information be required.

As it is impossible to cover all conditions of operation which arise in practice, customers are advised to carry out prototype testing wherever possible.

1.1 Characteristics and Advantages

DP4 is designed for use mainly under lubricated conditions. It shows

- an excellent wear resistance
- a low static and dynamic friction coefficient
- a high resistance to both cavitation and flow erosion damage of the polymer bearing surface by the lubricant
- DP4 is suitable for sliding, oscillating, reciprocating and rotating applications.
- DP4 is also suitable for use with non-lubricating fluids and in light duty unlubricated applications.

2 Structure and Composition

DP4 is a composite bearing material. It consists of a steel backing to which is bonded a porous sinter bronze interlayer which is overlaid and impregnated with Polytetrafluoroethylene (PTFE) containing a mixture of inorganic fillers and special polymer fibres. The steel backing provides mechanical strength and the bronze sinter layer provides a strong mechanical bond for the filled bearing lining.

DP4 was developed for high duty, oil lubricated, hydraulic applications as for example in automotive suspension McPherson struts and shock absorbers, hydraulic cyl-

inders, gear pumps and motors and axial and radial piston pumps and motors.




Fig. 1: DP4-microsection

2.1 Basic Forms

Standard Components

These products are manufactured to International, National or GGB standards. The following components are standard stock products:

- Cylindrical Bushes
- Flanged Bushes
- Strip Material



Fig. 2: Standard stock products

Non-Standard Components

These products are manufactured to customer's requirements and include for example:

- Modified Standard Components
- Thrust Washers
- Flanged Washers
- Half Bearings
- Flat Components
- Deep Drawn Parts
- Pressings
- Stampings



Fig. 3: Non-Standard Components

3 Properties

3.1 Physical and Mechanical Properties

		Symbol	Value	Unit	Comment
Physical Properties	Coefficient of linear thermal expansion :				
	parallel to surface	α_1	11	$1/10^6$ K	
	normal to surface	α_2	30	$1/10^6$ K	
	Maximum Operating Temperature	T_{max}	+280	°C	
	Minimum Operating Temperature	T_{min}	-200	°C	
Mechanical Properties	Compressive Yield Strength	σ_c	350	N/mm ²	measured on disc 5 mm diameter x 2.45 mm thick.
	Maximum Load				
	Static	$\bar{\rho}_{sta,max}$	250	N/mm ²	
	Dynamic	$\bar{\rho}_{dyn,max}$	140	N/mm ²	

Table 1: Physical and mechanical Properties of DP4

3.2 Chemical Properties

The following table provides an indication of the chemical resistance of DP4 to various chemical media.

It is recommended, that the chemical resistance is confirmed by testing if possible.

	Chemical	%	°C	Rating
Strong Acids	Hydrochloric Acid	5	20	-
	Nitric Acid	5	20	-
	Sulphuric Acid	5	20	-
Weak Acids	Acetic Acid	5	20	-
	Formic Acid	5	20	-
Bases	Ammonia	10	20	o
	Sodium Hydroxide	5	20	o
Solvents	Acetone		20	+
	Carbon Tetrachloride		20	+
Lubricants and fuels	Paraffin		20	+
	Gasolene		20	+
	Kerosene		20	+
	Diesel Fuel		20	+
	Mineral Oil		70	+
	HFA-ISO46 High Water Fluid		70	+
	HFC-Water-Glycol		70	+
	HFD-Phosphate Ester		70	+
	Water		20	o
	Sea Water		20	-

Table 2: Chemical resistance of DP4

+	<p>Satisfactory: Corrosion damage is unlikely to occur.</p>
o	<p>Acceptable: Some corrosion damage may occur but this will not be sufficient to impair either the structural integrity or the tribological performance of the material.</p>
-	<p>Unsatisfactory: Corrosion damage will occur and is likely to affect either the structural integrity and/or the tribological performance of the material.</p>

3.3 Frictional Properties

DP4 bearings show negligible 'stick-slip' and provide smooth sliding between adjacent surfaces. The coefficient of friction of DP4 depends upon:

- The specific load \bar{p} [N/mm²]
- The sliding speed U [m/s]
- The roughness of the mating running surface R_a [μm]
- The bearing temperature T [°C].

A typical relationship is shown in Fig. 4, which can be used as a guide to establish

the actual friction under clean, dry conditions after running in.

Exact values may vary by ±20 % depending on operating conditions. Before running in, the friction may be up to 50 % higher.

After progressively longer periods of dwell under load (e.g. hours or days) the static coefficient of friction on the first movement may be between 1.5 and 3 times greater, particularly before running in.

Effect of Temperature for unlubricated applications

The coefficient of friction of DP4 varies with temperature. Typical values are shown in Fig. 5 for temperatures up to 250 °C.

Friction increases at bearing temperatures below 0 °C.

Where frictional characteristics are critical to a design they should be established by prototype testing.




Fig. 4: Variation of friction coefficient f with specific load \bar{p} and speed U at temperature $T = 25$ °C




Fig. 5: Variation of friction coefficient f with specific load \bar{p} and temperature T at speed $U = 0.01$ m/s

4 Bearing Performance

4.1 McPherson Strut Applications

DP4 has been developed to provide improved wear, erosion resistance and reduced friction in McPherson strut piston rod guide bush applications under the most demanding of operating conditions.

In the following sections, the performance of DP4 is compared with that of the material used in the majority of this type of application.

Wear and Friction Properties

The wear and frictional performance of DP4 has been evaluated in the piston rod guide bush application of a McPherson strut shock absorber using the test rig shown in Fig. 6. The test conditions are

designed to simulate the operational duty of the test strut in service and differ in detail according to the strut manufacturer. The test conditions used are given in Table 3 and Table 4.

McPherson Strut Test Rig




Fig. 6: Principle of the Strut Test Rig

Strut Wear - Test conditions

Waveform	Sine
Frequency	2.5 Hz
Side Load	890 N
Test Duration	100 hours
Stroke	100 mm
Mean Diametral Clearance	0.06 mm
Lubricant	TEX 0358
Foot Valve Temperature	70 °C

Table 3: McPherson strut wear test conditions

Strut Friction - Test conditions

Waveform	Sine
Frequency	0.1 Hz
Side Load	600 N
Stroke	70 mm
Mean Diametral Clearance	0.06 mm
Lubricant	TEX 0358
Foot Valve Temperature	Ambient

Table 4: McPherson strut friction test conditions

The relative wear and frictional performance of DP4 tested under these conditions are shown in Figures 7-9. Actual results for the wear rate and friction are not quoted because these depend strongly on the

actual test conditions and design of the strut under test. The relative performance plots shown thus provide the best indication as to the benefits offered by DP4 in this class of application.




Fig. 7: Relative wear resistance




Fig. 9: Relative dynamic friction coefficient




Fig. 8: Relative static friction coefficient

Cavitation Erosion Resistance

Under certain operating conditions, the PTFE lining of the McPherson strut piston rod guide bush can suffer erosion damage, due to cavitation and flow erosion effects from the oil film within the bearing. The test

rig shown in Fig. 10 is designed to reproduce the cavitation erosion damage to the bearing lining of the test specimen. The test conditions are given in Table 5.




Fig. 10: Principle of the cavitation erosion test rig

Cavitation Erosion - Test Conditions

Amplitude	0.015 mm
Frequency	20 kHz
Separation	1 mm
Test Duration	30 minutes
Lubricant	TEX 0358
Temperature	Ambient

Table 5: Cavitation erosion test conditions

The relative resistance to cavitation damage of DP4 as evaluated on this test rig is shown in Fig. 11.




Fig. 11: Relative resistance to cavitation erosion

Flow Erosion Resistance

The test rig shown in Fig. 12 is designed to reproduce flow erosion damage to the bearing lining of the test specimen. The test conditions are given in Table 6.




Fig. 12: Principle of the flow erosion test rig

Flow Erosion - Test Conditions

Bearing Diameter	20 mm
Bearing Length	15 mm
Diametral Clearance	0.11 mm
Pressure	13.8 MPa
Flow Rate	5 l/min
Test Duration	20 hours
Shaft Surface Finish	0.15 $\mu\text{m} \pm 0.05$
Temperature	Ambient

Table 6: Flow erosion test conditions

The relative resistance to flow erosion damage of DP4 as evaluated on this test rig is shown in Fig. 13.




Fig. 13: Relative resistance to flow erosion

4.2 Hydraulic Applications

DP4 also shows excellent wear and frictional performance in a wide range of oil lubricated hydraulic applications.

The wear resistance of Glacier DP4 under steady load oil immersed boundary lubrica-

tion conditions has been evaluated using the test rig shown in Fig. 14. The test conditions are given in Table 7.

GGB Jupiter Test Rig




Fig. 14: Principle of the GGB Jupiter test rig

Lubricated Wear - Test Conditions

Bearing Diameter	20 mm
Bearing Length	15 mm
Mean Diametral Clearance	0.10 mm
Speed	0.11 m/s
Lubricant	ISO VG 46 hydraulic oil

Table 7: Lubricated wear test conditions

The relative $\bar{p}U$ limits with boundary lubrication of DP4 and the material used in many high performance hydraulic pump applications as determined from these

tests are shown in Fig. 15. The limiting $\bar{p}U$ depends upon the actual operating conditions and hence the relative performance only is given for guidance.




Fig. 15: Relative $\bar{p}U$ limits

4.3 Dry Wear Performance

Design Factors

The main parameters when determining the size or calculating the service life for a DP4 bearing are:

- Specific Load Limit \bar{p}_{lim}
- $\bar{p}U$ Factor
- Mating surface roughness R_a

- Mating surface material
- Temperature T
- Other environmental factors e.g. housing design, dirt, lubrication

The following calculation can be used to estimate the bearing service life of DP4 under dry running conditions.

Specific Load \bar{p}

For the purpose of assessing bearing performance the specific load \bar{p} is defined as the working load divided by the projected area of the bearing and is expressed in N/mm^2 .




Fig. 16: Projected Area

Cylindrical Bush

$$(4.3.1) \quad \bar{p} = \frac{F}{D_i \cdot B} \quad [N/mm^2]$$

Flanged Bush (Axial Loading)

$$(4.3.3) \quad \bar{p} = \frac{F}{0.04 \cdot (D_{fl}^2 - D_i^2)} \quad [N/mm^2]$$

Thrust Washer

$$(4.3.2) \quad \bar{p} = \frac{4F}{\pi \cdot (D_o^2 - D_i^2)} \quad [N/mm^2]$$

Slideway

$$(4.3.4) \quad \bar{p} = \frac{F}{L \cdot W} \quad [N/mm^2]$$

Specific Load Limit \bar{p}_{lim}

The maximum load which can be applied to a DP4 bearing can be expressed in terms of the Specific Load Limit, which depends on the type of the loading. It is highest under steady loads. Conditions of dynamic load or oscillating movement which produce fatigue stress in the bearing result in a reduction in the permissible Specific Load Limit.

In general the specific load on a DP4 bearing should not exceed the Specific Load Limits given in Table 8.

The values of Specific Load Limit specified in Table 8 assume good alignment between the bearing and mating surface (Fig. 33).

Maximum specific load \bar{p}_{lim}

Type of loading	\bar{p}_{lim} [N/mm ²]									
steady load, rotating movement	140									
steady load, oscillating movement	140	140	115	95	85	80	60	44	30	20
No. of movement cycles Q	1000	2000	4000	6000	8000	10 ⁴	10 ⁵	10 ⁶	10 ⁷	10 ⁸
dynamic load, rotating or oscillating movement	60	60	50	46	42	40	30	22	15	10
No. of load cycles Q	1000	2000	4000	6000	8000	10 ⁴	10 ⁵	10 ⁶	10 ⁷	10 ⁸

Table 8: Specific load limit

Permanent deformation of the DP4 bearing lining may occur at specific loads above 140 N/mm². Under these conditions DP4 should only be used after consulting our application engineers or with slow intermittent movements.

The permissible maximum load on a thrust washer is higher than that on the flange of a flanged bush, and under conditions of high axial loads a thrust washer should be specified.

Sliding Speed U

Speeds in excess of 2.5 m/s sometimes lead to overheating, and a running in procedure may be beneficial.

This could consist of a series of short runs progressively increasing in duration from an initial run of a few seconds.

Calculation of Sliding Speed U

Continuous Rotation

Bushes

$$(4.3.5) \quad U = \frac{D_i \cdot \pi \cdot N}{60 \cdot 10^3} \quad [\text{m/s}]$$

Thrust Washers

$$(4.3.6) \quad U = \frac{\frac{D_o + D_i}{2} \cdot \pi \cdot N}{60 \cdot 10^3} \quad [\text{m/s}]$$

Oscillating Movement

Bushes

$$(4.3.7) \quad U = \frac{D_i \cdot \pi}{60 \cdot 10^3} \cdot \frac{4\varphi \cdot N_{osz}}{360} \quad [\text{m/s}]$$

Thrust Washers

$$(4.3.8) \quad U = \frac{\frac{D_o + D_i}{2} \cdot \pi}{60 \cdot 10^3} \cdot \frac{4\varphi \cdot N_{osz}}{360} \quad [\text{m/s}]$$




Fig. 17: Oscillating cycle φ

$\bar{p}U$ Factor

The useful operating life of a DP4 bearing is governed by the $\bar{p}U$ factor, the product of the specific load \bar{p} [N/mm²] and the sliding speed U [m/s].

For thrust washers and flanged bush thrust faces the rubbing velocity at the mean diameter is used.

	DP4	Unit
\bar{p}	140	N/mm ²
U	2.5	m/s
$\bar{p}U$ continuous	0.5	N/mm ² x m/s
$\bar{p}U$ intermittent	1.0	N/mm ² x m/s

Table 9: Typical data \bar{p} , U , $\bar{p}U$

$\bar{p}U$ factors up to 1.0 N/mm² x m/s can be accommodated for short periods, whilst for continuous rating, $\bar{p}U$ factors up to 0.5 N/mm² x m/s can be used, depending upon the operating life required.

Calculation of $\bar{p}U$ Factor

(4.3.9) [N/mm² x m/s]

$$\bar{p}U = \bar{p} \cdot U$$

Application Factors

The following factors influence the bearing performance of DP4 and must be considered in calculating the required dimensions

Temperature

The useful life of a DP4 bearing depends upon the operating temperature.

Under dry running conditions frictional heat is generated at the rubbing surface of the bearing dependent on the $\bar{p}U$ condition. For a given $\bar{p}U$ factor the operating temperature of the bearing depends upon the temperature of the surrounding environ-

ment, the heat dissipation properties of the housing and the mating surface. Intermittent operation affects the heat dissipation from the assembly and hence the operating temperature of the bearing.

The effect of temperature on the operating life of DP4 bearings is indicated by the factor a_T shown in Table 10.

The effect of temperature on the operating life of DP4 bearings is indicated by the factor a_T shown in Table 10.

Mode of Operation	Nature of housing	Temperature of bearing environment T_{amb} [°C] and Temperature application factor a_T					
		25	60	100	150	200	280
Dry continuous operation	Average heat dissipating qualities	1.0	0.8	0.6	0.4	0.2	0.1
Dry continuous operation	Light pressings or isolated housing with poor heat dissipating qualities	0.5	0.4	0.3	0.2	0.1	-
Dry continuous operation	Non-metallic housings with bad heat dissipating qualities	0.3	0.3	0.2	0.1	-	-
Dry intermittent operation (duration less than 2 min, followed by a longer dwell period)	Average heat dissipating qualities	2.0	1.6	1.2	0.8	0.4	0.2

Table 10: Temperature application factor a_T

Mating Surface

The effect of mating surface material type on the operating life of DP4 bearings is indicated by the mating surface factor a_M and life correction constant a_L shown in Table 11.

Note:

The factor values given assume a mating surface finish of $\leq 0.4 \mu\text{m } R_a$.

- A ground surface is preferred to fine turned.
- Surfaces should be cleaned of abrasive particles after polishing.
- Cast iron surfaces should be ground to $< 0.3 \mu\text{m } R_a$.
- The grinding cut should be in the same direction as the bearing motion relative to the shaft.

Material	Mating Surface Factor a_M	Life correction constant a_L
Steel and Cast Iron		
Carbon Steel	1	400
Carbon Manganese Steel	1	400
Alloy Steel	1	400
Case Hardened Steel	1	400
Nitrided Steel	1	400
Salt bath nitrocarburised	1	400
Stainless Steel (7-10 % Ni, 17-20 % Cr)	2	400
Cast Iron ($0.3 \mu\text{m } R_a$)	1	400

Table 11: Mating surface factor a_M and life correction constant a_L

Bearing Size

The running clearance of a DP4 bearing increases with bearing diameter resulting in a proportionally smaller contact area between the shaft and bearing. This reduction in contact area has the effect of

increasing the actual unit load and hence $\bar{p}U$ factor. The bearing size factor (Fig. 18) is used in the design calculations to allow for this effect.




Fig. 18: Contact area between bearing and shaft




Fig. 19: Bearing size factor a_B

Bore Burnishing

Burnishing the bore of a DP4 bearing results in a reduction in the wear performance. The application factor a_C given in

Table 12 is used in the design calculation to allow for this effect. Machining DP4 is not recommended.

Degree of sizing	Application factor a_C	
Burnishing: Excess of burnishing tool diameter over mean bore size	0.025 mm	0.8
	0.038 mm	0.6
	0.050 mm	0.3

Table 12: Bore burnishing application factor a_C

Type of Load

The type of load is considered in formula (4.4.9), Page 18 and (4.4.10), Page 18.




Fig. 20: Steady load, bush stationary, shaft rotating




Fig. 21: Rotating load, shaft stationary, bush rotating

4.4 Calculation of Bearing Service Life

Where the size of a bearing is governed largely by the space available the following calculation can be used to determine

whether its useful life will satisfy the requirements. If the calculated life is inadequate, a redesign should be considered.

Specific load \bar{p}

Bushes

$$(4.4.1) \quad \bar{p} = \frac{F}{D_i \cdot B} \quad [\text{N/mm}^2]$$

Thrust Washers

$$(4.4.3) \quad \bar{p} = \frac{4F}{p \cdot (D_o^2 - D_i^2)} \quad [\text{N/mm}^2]$$

Flanged Bushes

$$(4.4.2) \quad \bar{p} = \frac{F}{0.04 \cdot (D_{fl}^2 - D_i^2)} \quad [\text{N/mm}^2]$$

High load factor a_E

If a_E is negative then the bearing is overloaded. Increase the bearing diameter and/or length.

$$(4.4.4) \quad a_E = \frac{\bar{p}_{lim} - \bar{p}}{\bar{p}_{lim}} \quad [-]$$

\bar{p}_{lim} see Tab. 8, page 14

Modified $\bar{p}U$ Factor

Bushes

$$(4.4.5) \quad \bar{p}U = \frac{5.25 \cdot 10^{-5} F \cdot N}{a_E \cdot B \cdot a_T \cdot a_M \cdot a_B} \quad [\text{N/mm}^2 \times \text{m/s}]$$

Flanged Bushes

$$(4.4.6) \quad \bar{p}U = \frac{6.5 \cdot 10^{-4} F \cdot N}{a_E \cdot (D_{fl} - D_i) \cdot a_T \cdot a_M \cdot a_B} \quad [\text{N/mm}^2 \times \text{m/s}]$$

Thrust Washers

$$(4.4.7) \quad \bar{p}U = \frac{3.34 \cdot 10^{-5} F \cdot N}{a_E \cdot (D_o - D_i) \cdot a_T \cdot a_M \cdot a_B} \quad [\text{N/mm}^2 \times \text{m/s}]$$

For oscillating movement, calculate the average rotational speed.

$$(4.4.8) \quad N_E = \frac{4\phi \cdot N_{osz}}{360} \quad [1/\text{min}]$$

Estimation of bearing life L_H

Bushes (Steady load)

$$(4.4.9) \quad L_H = \frac{265}{\bar{p}U} - a_L \quad [\text{h}]$$

Bushes (Rotating load)

$$(4.4.10) \quad L_H = \frac{530}{\bar{p}U} - a_L \quad [\text{h}]$$

Flanged Bushes (Axial load)

(4.4.11) [h]

$$L_H = \frac{175}{\bar{p}U} - a_L$$

a_L see Table 11, Page 16

Thrust Washers

(4.4.12) [h]

$$L_H = \frac{175}{\bar{p}U} - a_L$$

Bore Burnishing

If the DP4 bush is bore burnished then this must be allowed for in estimating the bearing life by the application factor a_C (Table 12, Page 17).

Estimated Bearing Life

(4.4.13) [h]

$$L_H = L_H \cdot a_C$$

a_C see Table 12, Page 17

For Oscillating Movements or Dynamic loads

Calculate estimated number of cycles Z_T

(4.4.14) [cycles]

$$Z_T = L_H \cdot N_{osz} \cdot 60$$

If the required bearing life is known, the total number of cycles can be determined.

Check that Z_T is less than total number of cycles Q for the operating specific load \bar{p}_{lim} (Table 8, Page 14).

If Z_T < Q, bearing life will be limited by wear after Z_T cycles.

If Z_T > Q, bearing life will be limited by fatigue after Z_T cycles.

(4.4.15) [cycles]

$$Z_T = L_H \cdot C \cdot 60$$

Slideways

Specific load factor

(4.4.16) [-]

$$a_{E1} = A - \frac{F}{\bar{p}_{lim}}$$

If negative the bearing is overloaded and the bearing area should be increased.

Speed, temperature and material application factor

(4.4.17) [-]

$$a_{E2} = \frac{280 \cdot a_T \cdot a_M}{F \cdot U}$$

a_T see Table 10, Page 15
a_M see Table 11, Page 16

Relative contact area factor

(4.4.18) [-]

$$a_{E3} = \frac{A}{A_M}$$

Estimated bearing life

(4.4.19) [-]

$$L_H = a_{E1} \cdot a_{E2} \cdot a_{E3} - a_L$$

Note:

Estimated bearing lives greater than 4000 hours are subject to error due to inaccuracies in the extrapolation of test data.

4 Bearing Performance

4.5 Worked Examples

Cylindrical Bush

Given:			
Load Details	Steady Load	Inside Diameter D_i	40 mm
	Continuous Rotation	Length B	30 mm
Shaft	Steel	Bearing Load F	5000 N
	Unlubricated at 25 °C	Rotational Speed N	25 1/min

Calculation Constants and Application Factors			
Specific Load Limit p_{lim}	140 N/mm ²	(Table 8, Page 14)	
Application Factor a_T	1.0	(Table 10, Page 15)	
Material Application Factor a_M	1.0	(Table 11, Page 16)	
Bearing Size Factor a_B	0.85	(Fig. 19, Page 17)	
Life Correction Constant a_L	400	(Table 11, Page 16)	

Calculation	Ref	Value
Specific Load p [N/mm ²]	(5.4.1), page 18	$\bar{p} = \frac{F}{D_i \cdot B} = \frac{5000}{40 \cdot 30} = 4.17$
Sliding Speed U [m/s]	(5.3.5), page 14	$U = \frac{D_i \cdot \pi \cdot N}{60 \cdot 10^3} = \frac{40 \cdot \pi \cdot 25}{60000} = 0.052$
High Load Factor a_E [-] (must be >0)	(5.4.4), page 18	$a_E = \frac{\bar{p}_{lim} - \bar{p}}{\bar{p}_{lim}} = \frac{140 - 4.17}{140} = 0.970$
Modified pU Factor [N/mm ² x m/s]	(5.4.5), page 18	$\bar{p}U = \frac{5.25 \cdot 10^{-5} \cdot F \cdot N}{a_E \cdot B \cdot a_T \cdot a_M \cdot a_B} = \frac{6.5625}{24.265} = 0.27$
Life L_H [h]	(5.4.9), page 18	$L_H = \frac{265}{\bar{p}U} - a_L = \frac{265}{0.27} - 400 = 581$

Thrust washer

Given:			
Load Details	Axial Load	Inside Diameter D_i	38 mm
	Continuous Rotation	Outside Diameter D_o	62 mm
Shaft	Steel	Bearing Load F	6500 N
	Unlubricated at 25 °C	Rotational Speed N	10 1/min

Calculation Constants and Application Factors			
Specific Load Limit p_{lim}	140 N/mm ²	(Table 8, Page 14)	
Application Factor a_T	1.0	(Table 10, Page 15)	
Material Application Factor a_M	1.0	(Table 11, Page 16)	
Bearing Size Factor a_B	0.85	(Fig. 19, Page 17)	
Life Correction Constant a_L	400	(Table 11, Page 16)	

Calculation	Ref	Value
Specific Load p [N/mm ²]	(5.4.3), page 18	$\bar{p} = \frac{4 \cdot F}{\pi \cdot (D_o^2 - D_i^2)} = \frac{4 \cdot 6500}{\pi \cdot (62^2 - 38^2)} = 3.45$
Sliding Speed U [m/s]	(5.3.6), page 14	$U = \frac{D_o + D_i}{2} \cdot \pi \cdot N = \frac{62 + 38}{2} \cdot \pi \cdot 10 = \frac{60 \cdot 10^3}{60 \cdot 10^3} = 0.026$
High Load Factor a_E [-] (must be >0)	(5.4.4), page 18	$a_E = \frac{\bar{p}_{lim} - \bar{p}}{\bar{p}_{lim}} = \frac{140 - 3.45}{140} = 0.975$
Modified pU Factor [N/mm ² x m/s]	(5.4.7), page 18	$\bar{p}U = \frac{3.34 \cdot 10^{-5} \cdot F \cdot N}{a_E \cdot (D_o - D_i) \cdot a_T \cdot a_M \cdot a_B} = \frac{2.171}{19.28} = 0.113$
Life L_H [h]	(5.4.17), page 19	$L_H = \frac{175}{\bar{p}U} - a_L = \frac{175}{0.113} - 400 = 1149$

Flanged Bush

Given:			
Load Details	Axial Load	Flange Outside Diameter D_H	23 mm
	Continuous Rotation	Inside Diameter D_i	15 mm
Shaft	Steel	Bearing Load F	250 N
	Unlubricated at 25 °C	Rotational Speed N	5 1/min


Calculation Constants and Application Factors			
Specific Load Limit p_{lim}	140 N/mm ²	(Table 8, Page 14)	
Application Factor a_T	1.0	(Table 10, Page 15)	
Material Application Factor a_M	1.0	(Table 11, Page 16)	
Bearing Size Factor a_B	1.0	(Fig. 19, Page 17)	
Life Correction Constant a_L	400	(Table 11, Page 16)	

Calculation	Ref	Value
Specific Load p [N/mm ²]	(5.4.2), page 18	$\bar{p} = \frac{F}{0.04 \cdot (D_H^2 - D_i^2)} = \frac{250}{0.04 \cdot (23^2 - 15^2)} = 20.55$
Sliding Speed U [m/s]	(5.3.6), page 14	$U = \frac{D_H + D_i}{2} \cdot \pi \cdot N = \frac{23 + 15}{2} \cdot \pi \cdot 5 = \frac{60 \cdot 10^3}{60 \cdot 10^3} = 0.005$
High Load Factor a_E [-] (must be >0)	(5.4.4), page 18	$a_E = \frac{\bar{p}_{lim} - \bar{p}}{\bar{p}_{lim}} = \frac{140 - 20.55}{140} = 0.853$
Modified pU Factor [N/mm ² x m/s]	(5.4.6), page 18	$\bar{p}U = \frac{6.5 \cdot 10^{-4} \cdot F \cdot N}{a_E \cdot (D_H - D_i) \cdot a_T \cdot a_M \cdot a_B} = \frac{0.8125}{6.82} = 0.119$
Life L_H [h]	(5.4.11), page 18	$L_H = \frac{175}{\bar{p}U} - a_L = \frac{175}{0.119} - 400 = 1071$

5 Data Sheet

Application: _____

5.1 Data for bearing design calculations



- Cylindrical Bush
 Flanged Bush
 Thrust Washer
 Slideplate
 Special (Sketch)
- Rotational movement
 Steady load
 Rotating load
 Oscillating movement
 Linear movement

Existing Design
 New Design

Quantity

Dimensions in mm

Inside Diameter D_i

Outside Diameter D_o

Length B

Flange Diameter D_f

Flange Thickness S_f

Length of slideplate L

Width of slideplate W

Thickness of slideplate S_s

Load

Radial load or specific load F [N]
 \bar{p} [N/mm²]

Axial load or specific load F [N]
 \bar{p} [N/mm²]

Movement

Rotational speed N [1/min]

Speed U [m/s]

Length of Stroke L_S [mm]

Frequency of Stroke [1/min]

Oscillating cycle φ [°]

Oscillating frequency N_{osz} [1/min]

Service hours per day

Continuous operation

Intermittent operation

Operating time

Days per year

Fits and Tolerances

Shaft D_j

Bearing Housing D_H

Operating Environment

Ambient temperature T_{amb} [°]

Housing with good heat transfer properties

Light pressing or insulated housing which poor heat transfer properties

Non metal housing with poor heat transfer properties

Alternate operation in water and dry

Mating surface

Material

Hardness HB/HRC

Surface finish R_a [μm]

Lubrication

Dry

Continuous lubrication

Process fluid lubrication

Initial lubrication only

Hydrodynamic conditions

Process Fluid

Lubricant

Dynamic viscosity η

Service life

Required service life L_H [h]

Customer Data
 Company: _____
 Street: _____

City: _____
 Post Code: _____

Project:
 Name: _____
 Tel.: _____

Date: _____
 Signature: _____
 Fax: _____

6 Lubrication

DP4 provides excellent performance in lubricated applications. The following sections describe the basics of lubrication and

provide guidance on the application of DP4 in such environments.

6.1 Lubricants

DP4 can be used with most fluids including:

- water
- lubricating oils
- engine oil
- turbine oil
- hydraulic fluid
- solvent
- refrigerants

In general, the fluid will be acceptable if it does not chemically attack the filled PTFE overlay or the porous bronze interlayer.

Where there is doubt about the suitability of a fluid, a simple test is to submerge a sample of DP4 material in the fluid for two to three weeks at 15-20 °C above the operating temperature.

The following will usually indicate that the fluid is not suitable for use with DP4:

- A significant change in the thickness of the DP4 material,
- A visible change in the bearing surface other than some discolouration or staining,
- A visible change in the microstructure of the bronze interlayer.

6.2 Tribology

There are three modes of lubricated bearing operation which relate to the thickness of the developed lubricant film between the bearing and the mating surface:

- Hydrodynamic lubrication
- Mixed film lubrication
- Boundary lubrication.

These three modes of operation depend upon:

- Bearing dimensions
- Clearance
- Load
- Speed
- Lubricant Viscosity
- Lubricant Flow

Hydrodynamic lubrication

Characterised by:

- Complete separation of the shaft from the bearing by the lubricant film
- Very low friction and no wear of the bearing or shaft since there is no contact
- Coefficients of friction of 0.001 to 0.01

Hydrodynamic conditions occur when

$$(6.2.1) \quad \bar{p} \leq \frac{U \cdot \eta}{7.5} \cdot \frac{B}{D_i} \quad [\text{N/mm}^2]$$

$$\bar{p} \leq \frac{U \cdot \eta}{7.5} \cdot \frac{B}{D_i}$$




Fig. 22: Hydrodynamic lubrication

Mixed film lubrication

Characterised by:

- Combination of hydrodynamic and boundary lubrication.
- Part of the load is carried by localised areas of self pressurised lubricant and the remainder supported by boundary lubrication.
- Friction and wear depend upon the degree of hydrodynamic support developed.

- DP4 provides low friction and high wear resistance to support the boundary lubricated element of the load.




Fig. 23: Mixed film lubrication

Boundary lubrication

Characterised by:

- Rubbing of the shaft against the bearing with virtually no lubricant separating the two surfaces.
- Bearing material selection is critical to performance.
- Shaft wear is likely due to contact between bearing and shaft.
- The excellent properties of DP4 material minimises wear under these conditions.
- The dynamic coefficient of friction with DP4 is typically 0.05 to 0.3 under boundary lubrication conditions.

- The static coefficient of friction with DP4 is typically slightly above the dynamic coefficient of friction under boundary lubrication conditions.




Fig. 24: Boundary lubrication

6.3 Characteristics of Lubricated Bearings

DP4 is particularly effective in the most demanding of lubricated applications

- **High load conditions**
In highly loaded applications operating under boundary or mixed film conditions DP4 shows excellent wear resistance and low friction.
- **Start up and shut down under load**
With insufficient speed to generate a hydrodynamic film the bearing will operate under boundary or mixed film conditions.
 - DP4 minimises wear
 - DP4 requires less start-up torque than conventional metallic bearings.

Note the following however:

If a DP4 bearing is required to run dry after running in water under non hydrodynamic conditions then the wear resistance will be substantially reduced due to an increased amount of bedding in wear.

In order to use Fig. 24

- Using the formula in Section 5:
 - Calculate the specific load \bar{p} ,
 - Calculate the shaft surface speed U.

where full hydrodynamic operation cannot be maintained, for example:

- **Sparse lubrication**
Many applications require the bearing to operate with less than the ideal lubricant supply, typically with splash or mist lubrication only.
DP4 requires significantly less lubricant than conventional metallic bearings.
- **Non lubricating fluids**
DP4 operates satisfactorily in low viscosity and non lubricating fluids such as water and some process fluids.

Fig. 25, Page 24 shows the three lubrication regimes discussed above plotted on a graph of sliding speed vs the ratio of specific load to lubricant viscosity.

- Using the viscosity temperature relationships presented in Table 13:
 - Determine the viscosity in centipoise of the lubricant.

Note:

Viscosity is a function of operating temperature. If the operating temperature of the fluid is unknown, a provisional temperature of 25 °C above ambient can be used.

6.4 Design Guidance

Temperature (°C)	cP														
	0	10	20	30	40	50	60	70	80	90	100	110	120	130	140
Lubricant															
ISO VG 32	310	146	77	44	27	18	13	9.3	7.0	5.5	4.4	3.6	3.0	2.5	2.2
ISO VG 46	570	247	121	67	40	25	17	12	9.0	6.9	5.4	4.4	3.6	3.0	2.6
ISO VG 68	940	395	190	102	59	37	24	17	12	9.3	7.2	5.8	4.7	3.9	3.3
ISO VG 100	2110	780	335	164	89	52	33	22	15	11.3	8.6	6.7	5.3	4.3	3.6
ISO VG 150	3600	1290	540	255	134	77	48	31	21	15	11	8.8	7.0	5.6	4.6
Diesel oil	4.6	4.0	3.4	3.0	2.6	2.3	2.0	1.7	1.4	1.1	0.95				
Petrol	0.6	0.56	0.52	0.48	0.44	0.40	0.36	0.33	0.31						
Kerosene	2.0	1.7	1.5	1.3	1.1	0.95	0.85	0.75	0.65	0.60	0.55				
Water	1.79	1.30	1.0	0.84	0.69	0.55	0.48	0.41	0.34	0.32	0.28				

Table 13: Viscosity

Explanation to Fig. 24

Area 1

The bearing will operate with boundary lubrication and $\bar{p}U$ factor will be the major determinant of bearing life. DP4 bearing performance can be calculated using the

method given in Section 5, although the result will probably underestimate the bearing life.

Area 2

The bearing will operate with mixed film lubrication and $\bar{p}U$ factor is no longer a significant parameter in determining the bear-

ing life. DP4 bearing performance will depend upon the nature of the fluid and the actual service conditions.




Fig. 25: Design guide for lubricated application

Area 3

The bearing will operate with hydrodynamic lubrication. Bearing wear will be determined only by the cleanliness of the

lubricant and the frequency of start up and shut down.

Area 4

These are the most demanding operating conditions. The bearing is operated under either high speed or high bearing load to viscosity ratio, or, a combination of both.

Bearing performance may be improved by the addition of one or more grooves to the bearing and a shaft surface finish $<0.05 \mu\text{m } R_a$.

These conditions may cause

- excessive operating temperature and/or
- high wear rate.

6.5 Clearances for lubricated operation

The recommended shaft and housing diameters given for standard DP4 bushes will provide sufficient clearance for applications operating with boundary lubrication.

sary to improve the fluid flow through the bearing by reducing the recommended shaft diameter by approximately 0.1 %, particularly when the shaft surface speed exceeds 2.5 m/s.

For bearings operating with mixed film or hydrodynamic lubrication it may be neces-

6.6 Grooving for lubricated operation

In demanding applications an axial oil groove will improve the performance of DP4. Fig. 26 shows the recommended form and location of a single groove with

respect to the applied load and the bearing split. GGB can manufacture special DP4 bearings with embossed or milled grooves on request.




Fig. 26: Location of grooves

6.7 Mating Surface Finish for lubricated operation

- $R_a \leq 0.4 \mu\text{m}$ Boundary lubrication
- $R_a = 0.1-0.2 \mu\text{m}$ Mixed film or hydrodynamic conditions
- $R_a \leq 0.05 \mu\text{m}$ for the most demanding operating conditions

6.8 Grease Lubrication

DP4 is not generally recommended for use with grease lubrication.

In particular the following must be avoided:

- Dynamic loads - which can result in erosion of the PTFE bearing surface.
- Greases with EP additives or fillers such as graphite or MoS_2 which can cause rapid wear of DP4.

7 Bearing Assembly

Dimensions and Tolerances

DP4 bushes are prefinished in the bore, and except in very exceptional circumstances, must not be burnished, broached or otherwise modified. It is essential that the correct running clearance is used and that both the diameter of the shaft and the bore of the housing are finished to the limits given in the tables. Under dry running conditions any increase in the clearances given will result in a proportional reduction in performance.

If the bearing housing is unusually flexible the bush will not close in by the calculated

amount and the running clearance will be more than the optimum. In these circumstances the housing should be bored slightly undersize or the journal diameter increased, the correct size being determined by experiment.

Where free running is essential, or where light loads (less than 0.1 N/mm²) prevail and the available torque is low, increased clearance is required and it is recommended that the shaft size quoted in the table be reduced by 0.025 mm.

7.1 Allowance for Thermal Expansion

For operation in high temperature environments the clearance should be increased by the amounts indicated by Fig. 27 to

compensate for the inward thermal expansion of the bearing lining.




Fig. 27: Increase in diametral clearance

If the housing is non-ferrous then the bore should be reduced by the amounts given in Table 14, in order to give an increased

interference fit to the bush, with a similar reduction in the journal diameter additional to that indicated by Fig. 27.

Housing material	Reduction in housing diameter per 100 °C rise	Reduction in shaft diameter per 100 °C rise
Aluminium alloys	0.1 %	0.1 % + values from Fig. 27
Copper base alloys	0.05 %	0.05 % + values from Fig. 27
Steel and cast iron	–	values from Fig. 27
Zinc base alloys	0.15 %	0.15 % + values from Fig. 27

Table 14: Allowance for high temperature

7.2 Tolerances for minimum clearance

Where it is required to keep the variation of assembled clearance to a minimum, closer tolerances can be specified towards the

upper end of the journal tolerance and the lower end of the housing tolerance.

If housings to H6 tolerance are used, then the journals should be finished to the following limits.

D_i	D_J
<25 mm	-0.019 -0.029
>25 mm < 50 mm	-0.021 -0.035

Table 15: Shaft tolerances for use with H6 housings

The sizes in Table 16 give the following nominal clearance range.

D_i	C_D
10 mm	0.005 - 0.078
50 mm	0.005 - 0.130

Table 16: Clearance vs bearing diameter

Sizing

The burnishing of the bore of an assembled DP4 bush in order to achieve a smaller clearance tolerance is only permissible if a substantial reduction in dry wear performance is acceptable. Fig. 28 shows a recommended burnishing tool for the sizing of DP4 bushes.

The coining section of the burnishing tool should be case hardened (case depth 0.6-1.2 mm, HRC 60±2) and polished ($R_z \approx 1\mu\text{m}$).

Note: Ball burnishing or fine boring of DP4 bushes is not recommended.

Assembled bush Inside- \varnothing	Required bush Inside- \varnothing	Required burnishing tool- $\varnothing D_C$
$D_{i,a}$	$D_{i,a} + 0.025$	$D_{i,a} + 0.06$
$D_{i,a}$	$D_{i,a} + 0.038$	$D_{i,a} + 0.08$
$D_{i,a}$	$D_{i,a} + 0.050$	$D_{i,a} + 0.1$

Table 17: Burnishing Tool Tolerances

The values given in Table 17 indicate the dimensions of the burnishing tool required to give specific increases in the bearing bore diameter.

Exact values must be determined by test.

The reduction in bearing performance as a result of burnishing is allowed for in the bearing life calculation by the application factor a_C (Table 12, Page 17).




Fig. 28: Burnishing Tool

7.3 Counterface Design

The suitability of mating surface materials and recommendations of mating surface finish for use with DP4 are discussed in detail on page 16.

DP4 is normally used in conjunction with ferrous journals and thrust faces, but in damp or corrosive surroundings, particularly without the protection of oil or grease, stainless steel, hard chromium plated mild steel, or hard anodised aluminium is recommended. When plated mating surfaces are specified the plating should possess

adequate strength and adhesion, particularly if the bearing is to operate with high fluctuating loads.

The shaft or thrust collar used in conjunction with the DP4 bush or thrust washer must extend beyond the bearing surface in order to avoid cutting into it. The mating surface must also be free from grooves or flats, the end of the shaft should be given a lead-in chamfer and all sharp edges or projections which may damage the soft overlay of the DP4 must be removed.




Fig. 29: Counterface design

7.4 Installation

Fitting of cylindrical Bushes




Fig. 30: Fitting of cylindrical bushes

Fitting of flanged bushes




Fig. 31: Fitting of flanged bushes

Insertion Forces




Fig. 32: Maximum insertion force F_i

Alignment

Accurate alignment is an important consideration for all bearing assemblies. With DP4 bearings misalignment over the

length of a bush (or pair of bushes), or over the diameter of a thrust washer should not exceed 0.020 mm as illustrated in Fig. 33.




Fig. 33: Alignment

Sealing

While Glacier DP4 can tolerate the ingress of some contaminant materials into the bearing without loss of performance, where there is the possibility of highly

abrasive material entering the bearing, a suitable sealing arrangement, as illustrated in Fig. 34 should be provided.




Fig. 34: Recommended sealing arrangements

7.5 Axial Location

Where axial location is necessary, it is advisable to fit DP4 thrust washers in con-

junction with DP4 bushes, even when the axial loads are low.

Fitting of Thrust Washers

DP4 thrust washers should be located in a recess as shown in Fig. 35. For the recess diameter the tolerance class [D10] is recommended. The recess depth is given in the product tables, page 40 and following.

If a recess is not possible one of the following methods may be used:

- Two dowel pins
- Two screws
- Adhesive
- Soldering (temperature <math><320\text{ }^\circ\text{C}</math>).

Important Note

- Ensure the washer ID does not touch the shaft after assembly
- Ensure that the washer is mounted with the steel backing to the housing
- Dowels pins should be recessed 0.25 mm below the bearing surface
- Screws should be countersunk 0.25 mm below the bearing surface
- DP4 must not be heated above 320 °C
- Contact adhesive manufacturers for guidance selection of suitable adhesives
- Protect the bearing surface to prevent contact with adhesive.




Fig. 35: Installation of Thrust-Washer

Grooves for Wear Debris Removal

Tests with thrust washers have demonstrated that for optimum dry wear performance at specific loads in excess of 35 N/mm², four wear debris removal grooves should be machined in the bearing surface as shown in Fig. 36.

Grooves in bushes have not been found to be beneficial in this respect.




Fig. 36: Debris removal Grooves

Slideways

DP4 strip material for use as slideway bearings should be installed using one of the following methods:

- Countersunk screws
- Adhesives
- Mechanical location as shown in Fig. 37.




Fig. 37: Mechanical location of DP4 slideplates

8 Modification

8.1 Cutting and Machining

The modification of DP4 bearing components requires no special procedures. In general it is more satisfactory to perform machining or drilling operations from the PTFE side in order to avoid burrs. When cutting is done from the steel side, the min-

imum cutting pressure should be used and care taken to ensure that any steel or bronze particles protruding into the remaining bearing material, and all burrs, are removed.

Drilling Oil Holes

Bushes should be adequately supported during the drilling operation to ensure that

no distortion is caused by the drilling pressure.

Cutting Strip Material

DP4 strip material may be cut to size by any one of the following methods.

Care must be taken to protect the bearing surface from damage and to ensure that no deformation of the strip occurs:

- Using side and face cutter, or slitting saw, with the strip held flat and securely

on a horizontal milling machine.

- Cropping
- Guillotine (For widths less than 90 mm only)
- Water-jet cutting
- Laser cutting (see Health Warning).

8.2 Electroplating

DP4 Components

In order to provide some protection in mildly corrosive environments the steel back and end faces of standard range DP4 bearings are tin flashed.

DP4 can be electroplated with most of the conventional electroplating metals including the following:


- zinc ISO 2081
- nickel ISO 1456
- hard chromium ISO 1456.

For the harder materials if the specified plating thickness exceeds approximately 5 μm then the housing diameter should be increased by twice the plating thickness in order to maintain the correct assembled bearing bore size.

Where electrolytic attack is possible tests should be conducted to ensure that all the materials in the bearing environment are mutually compatible.

9 Standard Products

9.1 DP4 Cylindrical bushes



All dimensions in mm

Outside Co and Inside Ci chamfers

Wall thickness s_3	C_o (a)		C_i (b)	Wall thickness s_3	C_o (a)		C_i (b)
	machined	rolled			machined	rolled	
0.75	0.5 ± 0.3	0.5 ± 0.3	-0.1 to -0.4	2	1.2 ± 0.4	1.0 ± 0.4	-0.1 to -0.7
1	0.6 ± 0.4	0.6 ± 0.4	-0.1 to -0.5	2.5	1.8 ± 0.6	1.2 ± 0.4	-0.2 to -1.0
1.5	0.6 ± 0.4	0.6 ± 0.4	-0.1 to -0.7				

a = Chamfer C_o machined or rolled at the opinion of the manufacturer

b = C_i can be a radius or a chamfer in accordance with ISO 13715

Part No.	Nominal size		Wall thickness s_3	Length B	Shaft- \varnothing D_J [h6, f7, h8]	Housing- \varnothing D_H [H6, H7]	Bush i- \varnothing $D_{i,a}$ when ass. in H7 housing	Clearance C_D
	D_i	D_o						
0203 DP4	2	3.5	0.745	3.25	h6	H6	+2.058	0.064
0303 DP4			0.725					
0306 DP4	3	4.5	0.750	6.25	h6	H6	+3.048	0.054
0404 DP4				5.75				
0410 DP4	4	5.5	0.730	4.25	h6	H6	+4.048	0.056
0505 DP4				3.75				
0508 DP4	5	7	1.005	10.25	f7	H7	5.055	0.077
0510 DP4				9.75				
0606 DP4	6	8	0.980	6.25	f7	H7	6.055	0.083
0608 DP4				5.75				
0610 DP4	7	9	0.980	8.25	f7	H7	7.055	0.083
0710 DP4				7.75				
				10.25				
				9.75				

9 Standard Products

Part No.	Nominal size		Wall thickness s_3	Length B	Shaft- \varnothing D_J [h6, f7, h8]		Housing- \varnothing D_H [H6, H7]	Bush i- \varnothing $D_{i,a}$ when ass. in H7 housing	Clearance C_D	
	D_i	D_o			max. min.	max. min.				max. min.
0806 DP4	8	10	1.005 0.980	6.25	f7	7.987 7.972	10.015 10.000	8.055 7.990	0.083 0.003	
0808 DP4				5.75						
0810 DP4				8.25						
0812 DP4				7.75						
1008 DP4	10	12		10.25	f7	9.987 9.972	12.018 12.000	10.058 9.990		0.086 0.003
1010 DP4				9.75						
1012 DP4				12.25						
1015 DP4				11.75						
1020 DP4				15.25						
1208 DP4				14.75						
1210 DP4	12	14		20.25	f7	11.984 11.966	14.018 14.000	12.058 11.990		0.092 0.006
1212 DP4				19.75						
1215 DP4			25.25							
1220 DP4			24.75							
1225 DP4			10.25							
1310 DP4			9.75							
1320 DP4	13	15	20.25	f7	12.984 12.966	15.018 15.000	13.058 12.990	0.092 0.006		
1405 DP4			19.75							
1410 DP4	14	16	5.25	f7	13.984 13.966	16.018 16.000	14.058 13.990	0.092 0.006		
1412 DP4			4.75							
1415 DP4			10.25							
1420 DP4			9.75							
1425 DP4			12.25							
1510 DP4			11.75							
1512 DP4	15	17	15.25	f7	14.984 14.966	17.018 17.000	15.058 14.990	0.092 0.006		
1515 DP4			14.75							
1520 DP4			20.25							
1525 DP4			19.75							
			25.25							


Part No.	Nominal size		Wall thickness s_3	Length B	Shaft- \varnothing D_J [h6, f7, h8]	Housing- \varnothing D_H [H6, H7]	Bush i- \varnothing $D_{i,a}$ when ass. in H7 housing	Clearance C_D				
	D_i	D_o							max. min.	max. min.	max. min.	max. min.
1610 DP4	16	18	1.005 0.980	10.25	f7	H7	16.058 15.990	0.092 0.006				
1612 DP4				9.75								
1615 DP4				12.25								
1620 DP4				11.75								
1625 DP4				15.25								
1720 DP4	17	19		20.25					15.984	18.018	17.061 16.990	
1810 DP4				14.75					15.984	18.000		
1815 DP4				20.25					16.984	19.021		18.061 17.990
1820 DP4				19.75					17.984	19.000		
1825 DP4				25.25					17.966	20.021		
2010 DP4	20	23	24.75	f7	H7	20.071 19.990	0.095 0.006					
2015 DP4			10.25									
2020 DP4			9.75									
2025 DP4			15.25									
2030 DP4			14.75									
2215 DP4	22	25	20.25					f7	H7	22.071 21.990	0.112 0.010	
2220 DP4			19.75									
2225 DP4			25.25									
2230 DP4			24.75									
2415 DP4			30.25									
2420 DP4	29.75											
2425 DP4	15.25	24	1.505 1.475	f7	H7	24.071 23.990	0.126 0.010					
2430 DP4	14.75											
2515 DP4	20.25											
2520 DP4	19.75											
2525 DP4	25.25											
2530 DP4	24.75											
2550 DP4	30.25	25						2.005 1.970	f7	H7	25.071 24.990	0.126 0.010
2815 DP4	29.75											
2820 DP4	15.25											
2825 DP4	14.75											
2830 DP4	20.25											
2830 DP4	19.75											
2830 DP4	25.25											
2830 DP4	24.75											
2830 DP4	30.25											
2830 DP4	29.75											

9 Standard Products

Part No.	Nominal size		Wall thickness s_3 max. min.	Length B max. min.	Shaft- \emptyset D_J [h6, f7, h8]		Housing- \emptyset D_H [H6, H7]		Bush i- \emptyset $D_{i,a}$ when ass. in H7 housing max. min.	Clearance C_D max. min.
	D_i	D_o			max. min.	max. min.	max. min.	max. min.		
3010 DP4	30	34	2.005 1.970	10.25	f7	29.980 29.959	H7	34.025 34.000	30.085 29.990	0.126 0.010
3015 DP4				9.75						
3020 DP4				15.25						
3025 DP4				14.75						
3030 DP4				20.25						
3040 DP4				19.75						
3220 DP4	32	36	2.005 1.970	20.25	f7	31.975 31.950	H7	36.025 36.000	32.085 31.990	0.135 0.015
3230 DP4				19.75						
3240 DP4				30.25 29.75						
3520 DP4	35	39	2.005 1.970	20.25	f7	34.975 34.950	H7	39.025 39.000	35.085 34.990	0.135 0.015
3530 DP4				19.75						
3535 DP4				30.25						
3540 DP4				29.75						
3550 DP4				35.25 34.75						
3720 DP4				40.25 39.75						
4020 DP4	40	44	2.005 1.970	50.25	f7	39.975 39.950	H7	44.025 44.000	40.085 39.990	0.135 0.015
4030 DP4				49.75						
4040 DP4				20.25 19.75						
4050 DP4				30.25 29.75						
4520 DP4				40.25 39.75						
4530 DP4				45.25 44.75						
4540 DP4	45	50	2.005 1.970	50.25	f7	44.975 44.950	H7	50.025 50.000	45.105 44.990	0.155 0.015
4545 DP4				49.75						
4550 DP4				20.25 19.75						
5020 DP4				30.25 29.75						
5030 DP4				40.25 39.75						
5040 DP4	50	55	2.505 2.460	50.25	f7	49.975 49.950	H7	55.030 55.000	50.110 49.990	0.160 0.015
5050 DP4				49.75						
5060 DP4				60.25 59.75						
5520 DP4				20.25 19.75						
5525 DP4	55	60	2.505 2.460	25.25	f7	54.970 54.940	H7	60.030 60.000	55.110 54.990	0.170 0.020
5530 DP4				24.75						
5540 DP4				30.25 29.75						
5550 DP4				40.25 39.75						
				50.25 49.75						

Part No.	Nominal size		Wall thickness s_3	Length B	Shaft- \emptyset D_J [h6, f7, h8]	Housing- \emptyset D_H [H6, H7]	Bush i- \emptyset $D_{i,a}$ when ass. in H7 housing	Clearance C_D																
	D_i	D_o							max. min.	max. min.	max. min.	max. min.	max. min.											
5555 DP4	55	60	2.505 2.460	55.25	f7	H7	54.970 54.940	60.030 60.000	0.170 0.020															
5560 DP4				54.75						59.75														
6020 DP4	60	65		20.25	f7	H7	59.970 59.940	65.030 65.000		60.110 59.990														
6030 DP4				19.75							29.75													
6040 DP4				30.25							40.25													
6050 DP4				29.75							39.75													
6060 DP4				40.25							50.25													
6070 DP4				49.75							60.25													
6530 DP4				65							70	59.75	f7	H7	64.970 64.940	70.030 70.000	65.110 64.990							
6550 DP4												70.25						49.75						
6570 DP4	69.75	70.25																						
7040 DP4	70	75		40.25			f7	H7		69.970 69.940	75.030 75.000	0.170 0.020												
7050 DP4			39.75	50.25																				
7070 DP4			49.75	70.25																				
7580 DP4	75	80	69.75	h8					H7	74.970 74.940	80.030 80.000				75.110 74.990									
8060 DP4	80	85	80.25							80.000 79.954	85.035 85.000				80.155 80.020	0.201 0.020								
80100 DP4			79.75														100.50							
8530 DP4			99.50														30.50							
8560 DP4	85	90	29.50		h8	H7				85.000 84.946	90.035 90.000				85.155 85.020									
85100 DP4			60.50													100.50								
9060 DP4			59.50													99.50								
90100 DP4	90	95	60.50							h8	H7				90.000 89.946	95.035 95.000	0.209 0.020							
9560 DP4			59.50															100.50						
95100 DP4			99.50				60.50																	
10050 DP4	95	100	59.50				h8	H7				95.000 94.946			100.035 100.000	95.155 95.020								
10060 DP4			50.50															100.50						
100115 DP4			49.50															99.50						
10060 DP4	100	105	60.50									h8			H7	100.000 99.946		105.035 105.000	0.209 0.020					
10060 DP4			59.50																	115.50				
100115 DP4			114.50																	60.50				
10560 DP4	105	110	59.50													h8		H7		105.000 104.946	110.035 110.000	105.155 105.020		
105115 DP4			115.50																				114.50	
11060 DP4			114.50																				60.50	
11060 DP4	110	115	59.50							h8	H7						110.000 109.946			115.035 115.000	0.209 0.020			
110115 DP4			115.50																			114.50		
11550 DP4			114.50																			50.50		
11550 DP4	115	120	49.50														h8			H7		115.000 114.946	120.035 120.000	115.155 115.020
11570 DP4			70.50																					

9.2 DP4 Flanged bushes



Dimensions and Tolerances according to ISO 3547 and GSP-Specifications

All dimensions in mm

Outside Co and Inside Ci chamfers

Wall thickness s ₃	C ₀ (a)		C _i (b)	Wall thickness s ₃	C ₀ (a)		C _i (b)
	machined	rolled			machined	rolled	
0.75	0.5 ± 0.3	0.5 ± 0.3	-0.1 to -0.4	2	1.2 ± 0.4	1.0 ± 0.4	-0.1 to -0.7
1	0.6 ± 0.4	0.6 ± 0.4	-0.1 to -0.5		1.8 ± 0.6	1.2 ± 0.4	-0.2 to -1.0
1.5	0.6 ± 0.4	0.6 ± 0.4	-0.1 to -0.7				


a = Chamfer C₀ machined or rolled at the opinion of the manufacturer

b = C_i can be a radius or a chamfer in accordance with ISO 13715

Part No.	Nominal size		Wall thickness s ₃	Flange thickness s _{fl}	Flange-ø D _{fl}	Length B	Shaft-ø D _J [f7]	Housing-ø D _H [H7]	Ass. Inside-ø D _{i,a}	Clearance C _D			
	D _i	D _o									max. min.	max. min.	max. min.
BB 0304 DP4	3	4,5	0.750 0.730	0.80 0.70	7.5 6.5	4,25 3,75	3.000 2.994	4.508 4.500	3.044 3.004	0.054 0.000			
BB 0404 DP4		5,5			9.5 8.5	4,25 3,75	4.000 3.992	5.508 5.500	4.044 4.004	0.056 0.000			
BB 0505 DP4	5	7	1.005 0.980	1.005 0.800	10,5 9,5	5,25 4,75	4.990 4.978	7.015 7.000	5.055 4.990	0.077 0.000			
BB 0604 DP4	6	8			12,5 11,5	4,25 3,75	5.990 5.978	8.015 8.000	6.055 5.990				
BB 0608 DP4					8,25 7,75	7.987 7.972	10.015 10.000	8.055 7.990					
BB 0806 DP4					5,75 5,25				8	10	15,5 14,5	7,75 7,25	9.987 9.972
BB 0808 DP4	9,75 9,25												
BB 0810 DP4	7,25 6,75	10			12	18,5 17,5	9,25 8,75	9.987 9.972			12.018 12.000	10.058 9.990	
BB 1007 DP4	12,25 11,75												
BB 1009 DP4	17,25 16,75						12	14	20,5 19,5	7,25 6,75	11.984 11.966	14.018 14.000	12.058 11.990
BB 1012 DP4	9,25 8,75												
BB 1017 DP4	12,25 11,75	12	14	20,5 19,5	17,25 16,75	11.984 11.966	14.018 14.000	12.058 11.990					
BB 1207 DP4	7,25 6,75												
BB 1209 DP4	9,25 8,75	14	16	22,5 21,5	9,25 8,75	13.984 13.966	16.018 16.000	14.058 13.990					
BB 1212 DP4	12,25 11,75												
BB 1217 DP4	17,25 16,75												
BB 1412 DP4	12,25 11,75												
BB 1417 DP4	17,25 16,75												

Part No.	Nominal size		Wall thickness s ₃	Flange thickness s _{fl}	Flange-ø D _{fl}	Length B	Shaft-ø D _J [f7]	Housing-ø D _H [H7]	Ass. Inside-ø D _{i,a}	Clearance C _D
	D _i	D _o	max. min.	max. min.	max. min.	max. min.	max. min.	max. min.	max. min.	max. min.
BB 1509 DP4	15	17	1.005 0.980	1.005 0.800	23.5 22.5	9.25	14.984 14.966	17.018 17.000	15.058 14.990	0.092 0.006
BB 1512 DP4						8.75				
BB 1517 DP4						12.25				
BB 1612 DP4	11.75									
BB 1617 DP4	17.25									
BB 1812 DP4	16.75									
BB 1817 DP4	12.25	1.000 0.800		26.5 25.5	17.25	17.984 17.966	20.021 20.000	18.061 17.990		
BB 1822 DP4	11.75									
BB 2012 DP4	22.25									
BB 2017 DP4	21.75	1.505 1.475	1.600 1.400	30.5 29.5	11.25	19.980 19.959	23.021 23.000	20.071 19.990		
BB 2022 DP4	11.75									
BB 2512 DP4	11.25									
BB 2517 DP4	16.75			35.5 34.5	24.980 24.959				28.021 28.000	25.071 24.990
BB 2522 DP4	16.25									
BB 3016 DP4	21.75									
BB 3026 DP4	21.25	2.005 1.970	2.100 1.800	42.5 41.5	16.25	29.980 29.959	34.025 34.000	30.085 29.990		
BB 3516 DP4	15.75									
BB 3526 DP4	26.25									
BB 4016 DP4	25.75			53.5 52.5	39.975 39.950				44.025 44.000	40.085 39.990
BB 4026 DP4	16.25									
BB 4516 DP4	15.75									
BB 4526 DP4	26.25	2.505 2.460	2.600 2.400	58.5 57.5	16.25	44.975 44.950	50.025 50.000	45.105 44.990		
	15.75									


9.3 DP4 Thrust Washers



All dimensions in mm

Part No.	Inside- \emptyset	Outside- \emptyset	Thickness	Locating Hole- \emptyset	Pitch Circle- \emptyset	Recess depth
	D_i	D_o	S_T	d_D	d_p	H_a
	max. min.	max. min.	max. min.	max. min.	max. min.	max. min.
WC 08 DP4	10.25 10.00	20.00 19.75	1.50 1.45	No Hole	No Hole	1.20 0.95
WC 10 DP4	12.25 12.00	24.00 23.75		1.875 1.625	18.12 17.88	
WC 12 DP4	14.25 14.00	26.00 25.75		2.375 2.125	20.12 19.88	
WC 14 DP4	16.25 16.00	30.00 29.75			22.12 21.88	
WC 16 DP4	18.25 18.00	32.00 31.75		3.375 3.125	25.12 24.88	
WC 18 DP4	20.25 20.00	36.00 35.75			28.12 27.88	
WC 20 DP4	22.25 22.00	38.00 37.75		4.375 4.125	30.12 29.88	
WC 22 DP4	24.25 24.00	42.00 41.75			33.12 32.88	
WC 24 DP4	26.25 26.00	44.00 43.75		61.12 60.88	35.12 34.88	
WC 25 DP4	28.25 28.00	48.00 47.75			38.12 37.88	
WC 30 DP4	32.25 32.00	54.00 53.75		2.00 1.95	43.12 42.88	
WC 35 DP4	38.25 38.00	62.00 61.75			50.12 49.88	
WC 40 DP4	42.25 42.00	66.00 65.75		76.12 75.88	54.12 53.88	
WC 45 DP4	48.25 48.00	74.00 73.75			61.12 60.88	
WC 50 DP4	52.25 52.00	78.00 77.75	1.70 1.45	65.12 64.88		
WC 60 DP4	62.25 62.00	90.00 89.75		76.12 75.88		


9.4 DP4 Flanged Thrust Washers



All dimensions in mm

Part No.	Inside- \varnothing D_i	Flange- \varnothing D_{fl}	Outside- \varnothing D_o	Locating Hole- \varnothing d_p	Thickness s_T
	max. min.	max. min.	max. min.	max. min.	max. min.
BS 40 DP4	40.70 40.20	44.00 43.90	75.0 74.5	65.0 64.5	2.02 1.98
BS 50 DP4	51.50 51.00	55.00 54.88	85.0 84.5	75.0 74.5	
BS 60 DP4	61.50 61.00	65.00 64.88	95.0 94.5	85.0 84.5	
BS 70 DP4	71.50 71.00	75.00 74.88	110.0 109.5	100.0 99.5	
BS 80 DP4	81.50 81.00	85.00 84.86	120.0 119.5	110.0 109.5	
BS 90 DP4	91.50 91.00	95.00 94.86	130.0 129.5	120.0 119.5	
BS 100 DP4	101.50	105.00	140.0	130.0	
	101.00	104.86	139.5	129.5	

9.5 DP4 Strip



All dimensions in mm

Part No.	Length L	Width W	Usable Width W_u	Thickness s_s
				max. min.
S 07090 DP4	500	100	90	0.740
S 10200 DP4				0.700
S 15240 DP4		227	215	1.010
S 20240 DP4				0.970
S 25240 DP4				1.510
				1.470
				1.980
				1.940
				2.460
				2.420

10 Test Methods

10.1 Measurement of Wrapped Bushes

It is not possible to accurately measure the external and internal diameters of a wrapped bush in the free condition. In its free state a wrapped bush will not be perfectly cylindrical and the butt joint may be open. When correctly installed in a housing the butt joint will be tightly closed and the bush will conform to the housing. For this reason the external diame-

ter and internal diameter of a wrapped bush can only be checked with special gauges and test equipment.

The checking methods are defined in ISO 3547 Part 1 and 2 and ISO 12306 respectively.

Test A of ISO 3547 Part 2

Checking the external diameter in a test machine with checking blocks and adjusting mandrel.

Test A of ISO 3547 Part 2 on 2015 DP4	
Test housing and mandrel $d_{ch,1}$	23.062 mm
Test load F_{ch}	4500 N
Limits for Δz	0 and -0.065 mm
Bush outside diameter D_o	23.035 to 23.075 mm

Table 18: Test A of ISO 3547 Part 2




Fig. 38: Test A, Data for drawing

Test B (alternatively to Test A)

Check external diameter with GO and NOGO ring gauges.

Test C

Checking the internal diameter of a bush pressed into a ring gauge, which nominal diameter corresponds to the dimension specified in table 5 of ISO 3547 Part 1.




Fig. 39: Test C, Data for drawing (example $D_i = 20$ mm)

Measurement of Wall Thickness (alternatively to Test C)

The wall thickness is measured at one, two or three positions axially according to the bearing dimensions.

B [mm]	X [mm]	measurement position
≤ 15	B/2	1
$> 15 \leq 50$	4	2
> 50	6	2

Table 19: Measurement position for wall thickness




Fig. 40: Wall thickness measurement position

Test D

Check external diameter by precision measuring tape.

GGB warrants that products described in this brochure are free from defects in workmanship and material but unless expressly agreed in writing GGB gives no warranty that these products are suitable for any particular purpose or for use under any specific conditions notwithstanding that such purpose would appear to be covered by this publication. GGB accepts no liability for any loss, damage, or expense whatsoever arising directly or indirectly from use of its products. All business undertaken by GGB is subject to its standard Conditions of Sale, copies of which are available upon request. GGB products are subject to continual development and GGB reserves the right to make changes in the specification and design of its products without prior notice.

GLACIER™ is a Trademark of GGB.

DP4™ is a Trademark of GGB.

Health Hazard - Warning

Fabrication

At temperatures up to 250 °C the polytetrafluoroethylene (PTFE) present in the lining material is completely inert so that even on the rare occasions in which DP4 bushes are drilled, or sized, after assembly there is no danger in boring or burnishing.

At higher temperatures however, small quantities of toxic fumes can be produced and the direct inhalation of these can cause an influenza type of illness which may not appear for some hours but which subsides without after-effects in 24-48 hours.

Such fumes can arise from PTFE particles picked up on the end of a cigarette. Therefore smoking should be prohibited where DP4 is being machined.