



Product Data

RUSTILO DWX 30

Issue Number 1
03/07/2002

Rust Preventative

DESCRIPTION

Castrol Rustilo DWX 30 is a powerful dewatering agent which, upon evaporation of the solvent, deposits an ultra-thin, slightly greasy film.

APPLICATION

Castrol Rustilo DWX 30 rapidly removes water from components which have been machined using soluble cutting fluids, or which have been washed or pickled. The very thin residual film provides effective protection against corrosion and suppresses any corrosive attack resulting from fingerprints on the components, but does not interfere with air gauging equipment.

Castrol Rustilo DWX 30 can also be used as a lubricant for mild pressworking, where corrosion protection without further treatment is required.

Although Rustilo DWX 30 can be applied by brushing or spraying, its dewatering action is most effective if the articles to be protected can be immersed in a dip tank. The protective film can be removed using Castrol aqueous or solvent based cleaners.

FEATURES

- Excellent water displacing and penetrating properties
- Fingerprint suppressant

BENEFITS

- Economical in application
- Thin film does not interfere with air gauging equipment



Product Data

RUSTILO DWX 30

TYPICAL PHYSICAL CHARACTERISTICS

Appearance	Clear, light brown fluid
Relative Density @ 20°C	0.795
Closed Flash Point (Abel) °C	40
Drying Time @ 20°C (to 95% solvent loss), mins	30
Film Thickness, microns	0.6
Coverage, m ² /litre	105
BS 1133 Section 6 Classification	TP 2b
Protection:	
Indoors	9 months
Outdoors	3 months

The period specified for outdoor use assumes primary protection from the elements by tarpaulin or another form of cover.

APPROVALS: Rolls Royce CSS 122

Health and Safety information sheets are available for all Castrol products from the address below:
Castrol (U.K.) Limited, Pipers Way, Swindon, Wiltshire SN3 1RE, England, Telephone:
Orders/Enquiries (08459)645111, Technical Enquiries (01793)452111, Fax (01793)491442

2 of 2

All reasonable care has been taken to ensure that the information contained in this publication is accurate as at the date of printing. It should be noted however that the information above may be affected by changes occurring subsequent to the date of printing in the blend formulation or methods of application of any of the products referred to or in the requirements of any specification approval relating to any such products.